

ATACRYL 25T60**PRODUCT DESCRIPTION**

Air-drying, polyacrylic and thermoplastic resin

CHEMICAL COMPOSITION

1-component toluene-based acrylic resin

APPLICATIONSIndustrial paints and varnishes
Road marking paints**PACKING**IBC-1000 KG
DRUM-200 KG
Bulk**TECHNICAL SPECIFICATIONS**

Specification	Value	Unit	Test Method
Solvent type	Toluen	-	-
Solid content	58-62	%	TS EN ISO 3251
Viscosity (Brookfield 25 °C)	6340-9850	cP	TS 6126 EN ISO 2555
Acid value	Max 16	mg KOH/g	TS 2366 EN ISO 2114
Color	Max 1	Gardner	TS EN ISO 4630
Density (20 °C)	0,99-1,03	gr/cm ³	TS EN ISO 2811-1

SOLUBILITY**Aceton** -Soluble**Toluen** -Soluble**Ksilen** -Soluble**White Sprit** -Insoluble**STORAGE CONDITIONS AND SHELF LIFE**

The resin should be stored in its original, unopened, and undamaged packaging in a dry environment at temperatures between 5–30 °C. Avoid exposure to direct sunlight. Under the specified storage conditions, the shelf life of the resin is 1 year.